Safety Data Sheet

BERGQUIST GAP PAD TGP 1500

SDS No. : 570812
V001.0
Revision: 11.02.2022
printing date: 04.11.2026

Section 1. Identification of the substance/preparation and of the company/undertaking

Product name:
BERGQUIST GAP PAD TGP 1500

Other means of identification:
BERGQUIST GAP PAD TGP 1500BERGQUIST GAP PAD TGP 1500
Product code:
IDH2482873
Recommended use of the chemical and restrictions on use

Intended use:
Thermal Conductive Material

Identification of manufacturer, importer or distributor
Manufacturer: The Bergquist Company
301 Washington Street West
Cannon Falls, MN 55009
United States
Tel: +1-507-263-3766
Fax: +1-952-835-0430

Importer: Henkel Thailand Ltd The Offices at Centralworld, 35th Floor, 999/9 Rama 1 Rd, Kwang Patumwan, Khet Patumwan, Bangkok 10330, Thailand. Phone : + 6622098000 Fax : +6622098008

E-mail address of person responsible for Safety Data Sheet:
ap-ua-psra.sea@henkel.com

Emergency information:
FOR EMERGENCIES ONLY (Spill, major leak, Fire, Exposure, or Accident). Call CHEMTREC: +1 703-741-5970

Section 2. Hazards identification

GHS Classification:

Substance or mixture is not classified as hazardous according to Globally Harmonized System(GHS).

GHS label elements:

Substance or mixture is not classified as hazardous according to Globally Harmonized System(GHS).

Section 3. Composition / information on ingredients

Substance or Mixture:
Mixture

Declaration of hazardous chemical:

Hazard component CAS-No.	Content	GHS Classification
Aluminium oxide - non fibrous form 1344-28-1	30- 60 %	
Aluminium hydroxide 21645-51-2	10- 30 %	
Carbon black 1333-86-4	0.1- 1 %	
octamethylcyclotetrasiloxane 556-67-2	< 0.1 %	Flammable liquids 3 H226 Toxic to reproduction 2 H361 Chronic hazards to the aquatic environment 1 H410

Section 4. First aid measures

Inhalation:
Move to fresh air. If symptoms persist, seek medical advice.

Skin contact:
Rinse with running water and soap.
Obtain medical attention if irritation persists.

Eye contact:
Rinse immediately with plenty of running water (for 10 minutes). Seek medical attention if necessary.

Ingestion:
Rinse mouth, drink 1-2 glasses of water, do not induce vomiting, consult a doctor.

Section 5. Fire fighting measures

Suitable extinguishing media:
water, carbon dioxide, foam, powder

Improper extinguishing media:
High pressure waterjet

Specific hazards arising from the chemical:
In case of fire, keep containers cool with water spray.
In the event of a fire, carbon monoxide (CO), carbon dioxide (CO2) and nitrogen oxides (NOx) can be released.
Silicon dioxide

Special protection equipment and precautions for firefighters:
Wear self-contained breathing apparatus and full protective clothing, such as turn-out gear.

Section 6. Accidental release measures

Personal precautions:

Avoid contact with skin and eyes.
Wear protective equipment.
Ensure adequate ventilation.

Environmental precautions:
Do not empty into drains / surface water / ground water.

Clean-up methods:
Keep in suitable and closed containers for disposal.
Sweep up spilled material. Avoid creating dust.
Scrape up as much material as possible.
Dispose of contaminated material as waste according to Section 13.

Section 7. Handling and storage

Handling:
Avoid skin and eye contact.
See advice in section 8

Storage:
Ensure good ventilation/extraction.
Keep container tightly sealed.
Refer to Technical Data Sheet
Protect from direct sunlight.

Section 8. Exposure controls / personal protection

Components with specific control parameters for workplace:

ALUMINUM METAL AND INSOLUBLE COMPOUNDS, RESPIRABLE FRACTION 1344-28-1	**Value type**	Time Weighted Average (TWA):
	mg/m³	1
	Remarks	ACGIH
ALPHA-ALUMINA, RESPIRABLE DUST 1344-28-1	**Value type**	Time Weighted Average (TWA):
	mg/m³	5
	Remarks	TH OEL
Particles (insoluble or poorly soluble) not otherwise specified, respirable particles 1344-28-1	**Value type**	Time Weighted Average (TWA):
	mg/m³	3
	Remarks	ACGIH
Particles (insoluble or poorly soluble) not otherwise specified, inhalable particles 1344-28-1	**Value type**	Time Weighted Average (TWA):
	mg/m³	10
	Remarks	ACGIH
ALPHA-ALUMINA, INHALABLE DUST 1344-28-1	**Value type**	Time Weighted Average (TWA):
	mg/m³	15
	Remarks	TH OEL
ALUMINUM METAL AND INSOLUBLE COMPOUNDS, RESPIRABLE FRACTION 21645-51-2	**Value type**	Time Weighted Average (TWA):
	mg/m³	1
	Remarks	ACGIH
Aluminium hydroxide 21645-51-2	**Value type**	Time Weighted Average (TWA):
	mg/m³	10
Particles (insoluble or poorly soluble) not otherwise specified, respirable particles 21645-51-2	**Value type**	Time Weighted Average (TWA):
	mg/m³	3
	Remarks	ACGIH
Particles (insoluble or poorly soluble) not otherwise specified, inhalable particles 21645-51-2	**Value type**	Time Weighted Average (TWA):
	mg/m³	10
	Remarks	ACGIH
CARBON BLACK, INHALABLE FRACTION 1333-86-4	**Value type**	Time Weighted Average (TWA):
	mg/m³	3
	Remarks	ACGIH

Respiratory protection:
Ensure adequate ventilation.
An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area
Filter type: A (EN 14387)

Hand protection:
Chemical-resistant protective gloves (EN 374).
Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374):
nitrile rubber (NBR; >= 0.4 mm thickness)
Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374):
nitrile rubber (NBR; >= 0.4 mm thickness)
This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g.

temperature). If signs of wear and tear are noticed then the gloves should be replaced.

Eye protection:
Wear protective glasses.
Protective eye equipment should conform to EN166.

Body protection:
Wear suitable protective clothing.
Protective clothing should conform to EN 14605 for liquid splashes or to EN 13982 for dusts.

Engineering controls:
Ensure good ventilation/extraction.

General protection and hygiene measures:
The workplace should be equipped with an emergency shower and eye-rinsing facility.

Hygienic measures:
Good industrial hygiene practices should be observed.
Wash hands before work breaks and after finishing work.
Do not eat, drink or smoke while working.

Section 9. Physical and chemical properties

Appearance:	Various solid
Odor:	slightly
Odor threshold (CA):	No data available.
pH:	No data available.
Melting point / freezing point:	No data available.
Specific gravity:	No data available.
Boiling point:	No data available.
Flash point:	Product is a solid.
Evaporation rate:	No data available.
Flammability (solid, gas):	No data available.
Lower explosive limit:	No data available.
Upper explosive limit:	No data available.
Vapor pressure:	No data available.
Vapor density:	No data available.
Density:	No data available.
Solubility:	No data available.
Partition coefficient: n-octanol/water:	No data available.
Auto ignition:	No data available.
Decomposition temperature:	No data available.
Viscosity:	No data available.
VOC content: (2010/75/EC)	< 1.00 %

Section 10. Stability and reactivity

Reactivity/Incompatible materials:
None if used for intended purpose.
Chemical stability:
Stable under recommended storage conditions.
Conditions to avoid:
Stable under normal conditions of storage and use.
Hazardous decomposition products:
carbon oxides.

Section 11. Toxicological information

Symptoms of Overexposure**:** None known.

Acute oral toxicity:

Aluminium oxide - non fibrous form 1344-28-1	Value type	LD50
	Value	> 10,000 mg/kg
	Species	rat
	Method	equivalent or similar to OECD Guideline 401 (Acute Oral Toxicity)
Aluminium hydroxide 21645-51-2	Value type	LD50
	Value	> 2,000 mg/kg
	Species	rat
	Method	OECD Guideline 423 (Acute Oral toxicity)
Carbon black 1333-86-4	Value type	LD50
	Value	> 8,000 mg/kg
	Species	rat
	Method	equivalent or similar to OECD Guideline 401 (Acute Oral Toxicity)
octamethylcyclotetrasiloxane 556-67-2	Value type	LD50
	Value	> 4,800 mg/kg
	Species	rat
	Method	equivalent or similar to OECD Guideline 401 (Acute Oral Toxicity)

Acute inhalative toxicity:

octamethylcyclotetrasiloxane 556-67-2	Value type	LC50
	Value	36 mg/l
	Exposure time	4 h
	Species	rat
	Method	OECD Guideline 403 (Acute Inhalation Toxicity)

Acute dermal toxicity:

octamethylcyclotetrasiloxane 556-67-2	Value type	LD50
	Value	> 2,375 mg/kg
	Species	rat
	Method	equivalent or similar to OECD Guideline 402 (Acute Dermal Toxicity)

Skin corrosion/irritation:

Aluminium oxide - non fibrous form 1344-28-1	Result	not irritating
	Exposure time	24 h
	Species	rabbit
	Method	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)
Aluminium hydroxide 21645-51-2	Result	not irritating
	Exposure time	4 h
	Species	rabbit
	Method	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)
Carbon black 1333-86-4	Result	not irritating
	Exposure time	4 h
	Species	rabbit
	Method	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)
octamethylcyclotetrasiloxane 556-67-2	Result	not irritating
	Exposure time	
	Species	rabbit
	Method	equivalent or similar to OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

Serious eye damage/irritation:

Aluminium oxide - non fibrous form 1344-28-1	Result	slightly irritating
	Exposure time	
	Species	rabbit
	Method	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Aluminium hydroxide 21645-51-2	Result	not irritating
	Exposure time	
	Species	rabbit
	Method	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Carbon black 1333-86-4	Result	not irritating
	Exposure time	
	Species	rabbit
	Method	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
octamethylcyclotetrasiloxane 556-67-2	Result	not irritating
	Exposure time	
	Species	rabbit
	Method	equivalent or similar to OECD Guideline 405 (Acute Eye Irritation / Corrosion)

Respiratory or skin sensitization:

Aluminium oxide - non fibrous form 1344-28-1	Result	not sensitising
	Test type	Draize Test
	Species	guinea pig
	Method	Landsteiner & Jacobs Method
Aluminium hydroxide 21645-51-2	Result	not sensitising
	Test type	Guinea pig maximisation test
	Species	guinea pig
	Method	OECD Guideline 406 (Skin Sensitisation)
Carbon black 1333-86-4	Result	not sensitising
	Test type	Mouse local lymphnode assay (LLNA)
	Species	mouse
	Method	OECD Guideline 429 (Skin Sensitisation: Local Lymph Node Assay)
octamethylcyclotetrasiloxane 556-67-2	Result	not sensitising
	Test type	Guinea pig maximisation test
	Species	guinea pig
	Method	OECD Guideline 406 (Skin Sensitisation)

Germ cell mutagenicity:

Aluminium oxide - non fibrous form 1344-28-1	Result	negative
	Type of study / Route of administration	in vitro mammalian chromosome aberration test
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Aluminium oxide - non fibrous form 1344-28-1	Result	negative
	Type of study / Route of administration	oral: gavage
	Metabolic activation / Exposure time	
	Species	rat
	Method	OECD Guideline 474 (Mammalian Erythrocyte Micronucleus Test)
Aluminium hydroxide 21645-51-2	Result	negative
	Type of study / Route of administration	mammalian cell gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Aluminium hydroxide 21645-51-2	Result	negative
	Type of study / Route of administration	oral: gavage
	Metabolic activation / Exposure time	
	Species	rat
	Method	OECD Guideline 474 (Mammalian Erythrocyte Micronucleus Test)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	bacterial reverse mutation assay (e.g Ames test)
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	mammalian cell gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	sister chromatid exchange assay in mammalian cells
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 479 (Genetic Toxicology: In Vitro Sister Chromatid Exchange Assay in Mammalian Cells)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	in vitro mammalian cell micronucleus test
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 487 (In vitro Mammalian Cell Micronucleus Test)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	mammalian cell gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 490 (In Vitro Mammalian Cell Gene Mutation Tests Using the Thymidine Kinase Gene)
Carbon black 1333-86-4	Result	negative
	Type of study / Route of administration	inhalation
	Metabolic activation / Exposure time	
	Species	rat
	Method	OECD Guideline 489 (In Vivo Mammalian Alkaline Comet Assay)
octamethylcyclotetrasiloxane 556-67-2	Result	negative
	Type of study / Route of administration	bacterial gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 471 (Bacterial Reverse Mutation Assay)
octamethylcyclotetrasiloxane 556-67-2	Result	negative
	Type of study / Route of administration	in vitro mammalian chromosome aberration test
	Metabolic activation / Exposure time	with and without
	Method	equivalent or similar to OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test)
octamethylcyclotetrasiloxane 556-67-2	Result	negative
	Type of study / Route of administration	mammalian cell gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	equivalent or similar to OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
octamethylcyclotetrasiloxane 556-67-2	Result	negative
	Type of study / Route of administration	inhalation

	Metabolic activation / Exposure time	
	Species	rat
	Method	equivalent or similar to OECD Guideline 475 (Mammalian Bone Marrow Chromosome Aberration Test)
octamethylcyclotetrasiloxane 556-67-2	Result	negative
	Type of study / Route of administration	oral: gavage
	Metabolic activation / Exposure time	
	Species	rat
	Method	equivalent or similar to OECD Guideline 478 (Genetic Toxicology: Rodent Dominant Lethal Test)

Repeated dose toxicity:

Aluminium oxide - non fibrous form 1344-28-1	Result	
	Route of application	inhalation: dust
	Exposure time / Frequency of treatment	
	Species	rat
	Method	OECD Guideline 413 (Subchronic Inhalation Toxicity: 90-Day)
Carbon black 1333-86-4	Result	NOAEL=> 1,000 mg/kg
	Route of application	oral: gavage
	Exposure time / Frequency of treatment	90 ddaily
	Species	rat
	Method	OECD Guideline 408 (Repeated Dose 90-Day Oral Toxicity in Rodents)
Carbon black 1333-86-4	Result	NOAEL=1 mg/m3
	Route of application	inhalation
	Exposure time / Frequency of treatment	13 w6 h/d, 5 d/w
	Species	rat
	Method	not specified
octamethylcyclotetrasiloxane 556-67-2	Result	LOAEL=35 ppm
	Route of application	inhalation
	Exposure time / Frequency of treatment	6 h nose only inhalation5 days/week for 13 weeks
	Species	rat
	Method	OECD Guideline 412 (Repeated Dose Inhalation Toxicity: 28/14-Day)
octamethylcyclotetrasiloxane 556-67-2	Result	NOAEL=960 mg/kg
	Route of application	dermal
	Exposure time / Frequency of treatment	3 w5 d/w
	Species	rabbit
	Method	equivalent or similar to OECD Guideline 410 (Repeated Dose Dermal Toxicity: 21/28-Day Study)

Section 12. Ecological information

General ecological information: Do not empty into drains / surface water / ground water.

Toxicity:

Aluminium oxide - non fibrous form 1344-28-1	Value type	LC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Fish
	Exposure time	96 h
	Species	Salmo trutta
	Method	OECD Guideline 203 (Fish, Acute Toxicity Test)
Aluminium oxide - non fibrous form 1344-28-1	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Daphnia
	Exposure time	48 h
	Species	Daphnia magna
	Method	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Aluminium oxide - non fibrous form 1344-28-1	Value type	NOEC
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Selenastrum capricornutum (new name: Pseudokirchneriella subcapitata)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
	Value type	EC50
	Value	Toxicity > Water solubility

	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Selenastrum capricornutum (new name: Pseudokirchneriella subcapitata)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Aluminium oxide - non fibrous form 1344-28-1	Value type	EC0
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Bacteria
	Exposure time	
	Species	not specified
	Method	not specified
Aluminium hydroxide 21645-51-2	Value type	LC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Fish
	Exposure time	48 h
	Species	Leuciscus idus
	Method	DIN 38412-15
	Value type	NOEC
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Fish
	Exposure time	33 d
	Species	Pimephales promelas
	Method	OECD Guideline 210 (fish early lite stage toxicity test)
Aluminium hydroxide 21645-51-2	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Daphnia
	Exposure time	24 h
	Species	Daphnia magna
	Method	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Aluminium hydroxide 21645-51-2	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Pseudokirchneriella subcapitata
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Carbon black 1333-86-4	Value type	LC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Fish
	Exposure time	96 h
	Species	Brachydanio rerio (new name: Danio rerio)
	Method	OECD Guideline 203 (Fish, Acute Toxicity Test)
Carbon black 1333-86-4	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Daphnia
	Exposure time	24 h
	Species	Daphnia magna
	Method	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Carbon black 1333-86-4	Value type	NOEC
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Scenedesmus subspicatus (new name: Desmodesmus subspicatus)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Scenedesmus subspicatus (new name: Desmodesmus subspicatus)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Carbon black 1333-86-4	Value type	EC0
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Bacteria
	Exposure time	3 h
	Species	activated sludge, domestic
	Method	OECD Guideline 209 (Activated Sludge, Respiration Inhibition Test)
octamethylcyclotetrasiloxane 556-67-2	Value type	NOEC
	Value	0.0044 mg/l
	Acute Toxicity Study	Fish
	Exposure time	93 d
	Species	Salmo gairdneri (new name: Oncorhynchus mykiss)
	Method	EPA OPPTS 797.1600 (Fish Early Life Stage Toxicity Test)

	Value type	LC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Fish
	Exposure time	96 h
	Species	Oncorhynchus mykiss
	Method	EPA OTS 797.1400 (Fish Acute Toxicity Test)
octamethylcyclotetrasiloxane 556-67-2	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Daphnia
	Exposure time	48 h
	Species	Daphnia magna
	Method	EPA OTS 797.1300 (Aquatic Invertebrate Acute Toxicity Test, Freshwater Daphnids)
octamethylcyclotetrasiloxane 556-67-2	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Algae
	Exposure time	96 h
	Species	Selenastrum capricornutum (new name: Pseudokirchneriella subcapitata)
	Method	EPA OTS 797.1050 (Algal Toxicity, Tiers I and II)
	Value type	EC10
	Value	0.022 mg/l
	Acute Toxicity Study	Algae
	Exposure time	96 h
	Species	Selenastrum capricornutum (new name: Pseudokirchneriella subcapitata)
	Method	EPA OTS 797.1050 (Algal Toxicity, Tiers I and II)
octamethylcyclotetrasiloxane 556-67-2	Value type	EC50
	Value	Toxicity > Water solubility
	Acute Toxicity Study	Bacteria
	Exposure time	3 h
	Species	activated sludge
	Method	ISO 8192 (Test for Inhibition of Oxygen Consumption by Activated Sludge)

Persistence and degradability:

octamethylcyclotetrasiloxane 556-67-2	Result	not readily biodegradable.
	Route of application	aerobic
	Degradability	3.7 %
	Method	OECD Guideline 310 (Ready BiodegradabilityCO2 in Sealed Vessels (Headspace Test)

Bioaccumulative potential / Mobility in soil:

Aluminium hydroxide 21645-51-2	LogPow	-0.12
	Temperature	
	Method	QSAR (Quantitative Structure Activity Relationship)
octamethylcyclotetrasiloxane 556-67-2	Bioconcentration factor (BCF)	12,400
	Exposure time	28 d
	Species	Pimephales promelas
	Temperature	
	Method	EPA OTS 797.1520 (Fish Bioconcentration Test-Rainbow Trout)
octamethylcyclotetrasiloxane 556-67-2	LogPow	6.488
	Temperature	25.1 °C
	Method	OECD Guideline 123 (Partition Coefficient (1-Octanol / Water), Slow-Stirring Method)

Section 13. Disposal considerations

Product

Method of disposal:
Dispose of in accordance with local and national regulations.

Packaging

Disposal of uncleaned packages:
Packaging that cannot be cleaned are to be disposed of in the same manner as the product.

Section 14. Transport information

Road transport ADR:
Not dangerous goods

Railroad transport RID:
Not dangerous goods

Inland water transport ADN:
Not dangerous goods

Marine transport IMDG:
Not dangerous goods

Air transport IATA:
Not dangerous goods

`Section 15. Regulatory information

Regulatory Information:
Ministry of Industry Notice. The system to classify and communicate the hazard of hazardous material, BE. 2555

Global inventory status:

Regulatory list	Notification
ENCS (JP)	yes
ISHL (JP)	yes
CH INV	yes
EINECS	yes

Section 16. Other information

Disclaimer:
This Safety Data Sheet has been generated based on Ministry of Industry Notice. The system to classify and communicate the hazard of hazardous material, BE. 2555 only. No warranty or representation of any kind is given with respect to the substantive or export laws of any other jurisdiction or country. Please confirm that the information provided herein conforms to the substantive export or other law of any other jurisdiction prior to export. Please contact Henkel Product Safety and Regulatory Affairs for additional assistance.This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.
Dear Customer,
Henkel is committed to creating a sustainable future by promoting opportunities along the entire value chain. If you would like to contribute by switching from a paper to the electronic version of SDS, please contact the local Customer Service representative. We recommend to use a non-personal email address (e.g. SDS@your_company.com).